



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) EP 1 155 147 A1

(12)

# EUROPEAN PATENT APPLICATION

(43) Date of publication:  
21.11.2001 Bulletin 2001/47

(51) Int Cl.7: D04H 13/00, B32B 5/26,  
D04H 5/00

(21) Application number: 00304179.5

(22) Date of filing: 17.05.2000

(84) Designated Contracting States:  
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE  
Designated Extension States:  
AL LT LV MK RO SI

(71) Applicant: KANG NA HSIUNG ENTERPRISE CO.  
LTD.  
Tainan Hsien (TW)

(72) Inventors:  
• Tai, Jung Chi  
Chiali Chen, Tainan Hsien (TW)  
• Hu, Alvin Yen-Jung  
Hsinchu (TW)

(74) Representative: Nash, David Allen et al  
Haseltine Lake & Co.,  
Imperial House, 15-19 Kingsway  
London WC2B 6UD (GB)

(54) **Non-woven composite fabric**

(57) The present invention provides a non-woven composite fabric and a process for preparing the same. The non-woven fabric includes at least three webs which are consolidated together. At least one web is an

air-laid web, and at least one web is a spunbonded web or a meltblown web. The present invention can use a functional air-laid web in order to impart the non-woven composite fabric with various functions.

EP 1 155 147 A1

## EP 1 156 147 A1

## Description

BACKGROUND OF THE INVENTION

## 1. Field of the Invention:

[0001] The present invention relates to a non-woven composite fabric and a process for preparing the same, and more particularly to a non-woven composite fabric including at least three webs, in which at least one web is an air-laid web.

## 2. Description of the Prior Art:

[0002] Non-woven fabrics have been extensively used in household and medical applications. For example, such fabrics have been used as disposable diapers, sanitary napkins, and surgical clothes. A non-woven fabric can be formed by consolidating a multiple layers of webs. For example, in Taiwan Patent Publication No. 375664, a spunbonded/meltblown multi-layered non-woven composite fabric has been disclosed, which includes a spunbonded web/ at least one meltblown web/a spunbonded web, in which the average diameter of the fiber of the meltblown web is far finer than that of the fiber of the spunbonded web. This non-woven composite fabric is relatively good on barrier properties, but other properties still need further improvement.

SUMMARY OF THE INVENTION

[0003] Therefore, the object of the present invention is to provide a novel non-woven composite fabric. The present invention can use a functional air-laid web in order to impart the non-woven composite fabric with various functions.

[0004] To achieve the above object, the non-woven composite fabric of the present invention includes at least three webs which are consolidated together. At least one web is an air-laid web, and at least one web is a web selected from the group consisting of a spunbonded web and a meltblown web.

DETAILED DESCRIPTION OF THE INVENTION

[0005] The non-woven composite fabric of the present invention includes at least three webs which are consolidated together. At least one web is an air-laid web, and at least one web is a spunbonded web or a meltblown web.

[0006] The non-woven composite fabric of the present invention can have various combinations. For example, the non-woven composite fabric can include an air-laid web (abbreviated to A), a spunbonded web (abbreviated to S), and a meltblown web (abbreviated to M). One representative example of such a non-woven composite fabric includes a spunbonded web, a meltblown web, and an air-laid web laminated in order, such that an SMA non-woven fabric is formed. Another representative non-woven composite fabric includes a spunbonded web, an air-laid web, and a meltblown web laminated in order, such that an SAM non-woven fabric is formed.

[0007] Alternatively, the non-woven composite fabric of the present invention can include an air-laid web and two spunbonded webs. A representative example includes a spunbonded web, an air-laid web, and a spunbonded web laminated in order, such that an SAS non-woven fabric is formed.

[0008] Alternatively, the non-woven composite fabric of the present invention can include an air-laid web, a meltblown web, and two spunbonded webs. A representative example includes a spunbonded web, a meltblown web, an air-laid web, and a spunbonded web laminated in order, such that an SMAS non-woven fabric is formed.

[0009] Alternatively, the non-woven composite fabric of the present invention can include a spunbonded web, a meltblown web, an air-laid web, a meltblown web, and a spunbonded web laminated in order, such that an SMAMS non-woven fabric is formed.

[0010] The air-laid web used in the present invention can be formed by subjecting a raw material in the form of fibers, particles, or powders to an air-laying process. Suitable raw material can be pulp, activated carbon fibers or powders, super absorbent polymer (SAP) fibers or powders, hot melt adhesive fibers or powders, water-absorbent fibers, particles, or powders, oil-absorbent fibers or powders, chemical adsorbent fibers or particles, deodorant fibers or powders, or mixture thereof.

[0011] According to the present invention, a functional raw material can be subjected to air-laying to obtain a functional air-laid web. Then, the functional air-laid web can be used in order to impart the composite non-woven fabric with various functions. For example, when the raw material for the air-laid web is pulp or a super absorbent polymer, it can impart the composite non-woven fabric with absorption. When the raw material for the air-laid web includes pulp and a super absorbent polymer, the absorption of the composite non-woven fabric can be further improved. When the raw material for the air-laid web is activated carbon fibers (or particles or powders), it can impart the composite non-

## EP 1 156 147 A1

woven fabric with chemical adsorption. When the raw material for the air-laid web includes pulp and hot melt adhesive powders, high stiffness can be imparted to the fabric. When the raw material is adsorbent fibers or powders, chemical adsorption can be imparted to the fabric.

[0012] In the above-mentioned SMA non-woven fabric, if the raw material for the air-laid web is an absorbent material (such as a super absorbent polymer), since the air-laid web in the outer layer can provide absorption and the meltblown web in the inner layer has water repellency, such an SMA non-woven fabric can be used as a sanitary napkin material. In addition, in the above-mentioned SAM non-woven fabric, if the raw material for the air-laid web is an absorbent material (such as a super absorbent polymer), since the air-laid web in the inner layer can provide absorption and the meltblown web in the outer layer has water repellency, such an SAM non-woven fabric can be used as surgical clothes.

[0013] The spunbonded web used in the present invention can be composed of mono-component fiber or bi-component fiber of a melt spinning polymer. Also, the meltblown web used in the present invention can be composed of mono-component fiber or bi-component fiber of a melt spinning polymer.

[0014] Suitable melt spinning polymer can be polypropylene (PP), polyethylene (PE), polyethylene terephthalate (PET), polybutylene terephthalate (PBT), a copolymer of polypropylene (COPP), a copolymer of polyethylene terephthalate (COPET), a copolymer of polybutylene terephthalate (COPBT), or a polyamide.

[0015] When the fiber of the spunbonded web or the meltblown web of the present invention is a bi-component fiber, such bi-component fiber can be made of polypropylene/polyethylene (PP/PE), polyethylene terephthalate/polyethylene (PET/PE), polyethylene terephthalate/polypropylene (PET/PP), polypropylene/a copolymer of polypropylene (PP/COPP), polyethylene terephthalate/a copolymer of polyethylene terephthalate (PET/COPET), or a higher melting polyamide/a lower melting polyamide.

[0016] The bi-component fiber of the melt spinning polymer can include a lower melting component and a higher melting component. At that time, the fiber can be of sheath and core type or side by side type.

[0017] Alternatively, the bi-component fiber can be a micro fiber, such as split type micro fiber or sea and island micro fiber.

[0018] The present invention also provides a process for preparing a non-woven composite fabric. First, at least three webs are formed, in which at least one web is an air-laid web, and at least one web is a spunbonded web or a meltblown web. Then, the at least three webs are consolidated together to form a non-woven composite fabric. Suitable consolidating method is not limited and can be thermo-bonding, hot air-through bonding, water-jet entangling, ultrasonic bonding, and high frequency wave bonding.

[0019] The following examples are intended to illustrate the process and the advantages of the present invention more fully without limiting its scope, since numerous modifications and variations will be apparent to those skilled in the art.

### Example 1

[0020] The bottom layer was a spunbonded web (abbreviated to S) having a weight basis of 10 g/cm<sup>2</sup>. A meltblown web (20 g/cm<sup>2</sup>) (abbreviated to M) was laid onto the bottom layer as the second layer. Then, an air-laid web (250 g/cm<sup>2</sup>) (abbreviated to A) was laid onto the second layer as the third layer. Finally, a spunbonded web (20 g/cm<sup>2</sup>) (abbreviated to S) was laid onto the third layer as the fourth layer. The four-layered laminate was thermally bonded together to form an SMAS composite non-woven fabric. The properties are shown in Table 1.

[0021] From Table 1, it can be seen that the properties of the composite non-woven fabric of the present invention meet the CNS standard.

Table 1.

The properties of the SMAS non-woven fabric		
Properties	SMAS of the present invention	CNS standard
Longitude Penetration length (cm)	6.8	N.A.
Rewet (g)	0.065	< 2g
Hydro head (cm H <sub>2</sub> O)	57.6	N.A.
Air permeability (L/M <sup>2</sup> -sec)	11,513	N.A.
Moisture permeability (g/m <sup>2</sup> ×24hr)	9,320	N.A.

[0022] The foregoing description of the preferred embodiments of this invention has been presented for purposes of illustration and description. Obvious modifications or variations are possible in light of the above teaching. The

## EP 1 156 147 A1

embodiments were chosen and described to provide the best illustration of the principles of this invention and its practical application to thereby enable those skilled in the art to utilize the invention in various embodiments and with various modifications as are suited to the particular use contemplated. All such modifications and variations are within the scope of the present invention as determined by the appended claims when interpreted in accordance with the breadth to which they are fairly, legally, and equitably entitled.

## Claims

## 1. A non-woven composite fabric, comprising:

at least three webs which are consolidated together, wherein at least one web is an air-laid web, and at least one web is a web selected from the group consisting of a spunbonded web and a meltblown web.

2. The non-woven composite fabric as claimed in claim 1, which includes an air-laid web, a spunbonded web, and a meltblown web.

3. The non-woven composite fabric as claimed in claim 2, which includes a spunbonded web, a meltblown web, and an air-laid web laminated in order.

4. The non-woven composite fabric as claimed in claim 2, which includes a spunbonded web, an air-laid web, and a meltblown web laminated in order.

5. The non-woven composite fabric as claimed in claim 1, which includes an air-laid web and two spunbonded webs.

6. The non-woven composite fabric as claimed in claim 5, which includes a spunbonded web, an air-laid web, and a spunbonded web laminated in order.

7. The non-woven composite fabric as claimed in claim 1, which includes an air-laid web, a meltblown web, and two spunbonded webs.

8. The non-woven composite fabric as claimed in claim 7, which includes a spunbonded web, a meltblown web, an air-laid web, and a spunbonded web laminated in order.

9. The non-woven composite fabric as claimed in claim 1, which includes a spunbonded web, a meltblown web, an air-laid web, a meltblown web, and a spunbonded web laminated in order.

10. The non-woven composite fabric as claimed in claim 1, wherein the air-laid web is made of a material selected from the group consisting of pulp, activated carbon fibers or powders, super absorbent polymer fibers or powders, hot melt adhesive fibers or powders, water-absorbent fibers, particles, or powders, oil-absorbent fibers or powders, chemical adsorbent fibers or particles, deodorant fibers or powders, and mixture thereof.

11. The non-woven composite fabric as claimed in claim 1, wherein the spunbonded web is composed of mono-component fiber or bi-component fiber of a melt spinning polymer.

12. The non-woven composite fabric as claimed in claim 1, wherein the meltblown web is composed of mono-component fiber or bi-component fiber of a melt spinning polymer.

13. The non-woven composite fabric as claimed in claim 11 or 12, wherein the melt spinning polymer is selected from the group consisting of polypropylene (PP), polyethylene (PE), polyethylene terephthalate (PET), polybutylene terephthalate (PBT), a copolymer of polypropylene (COPP), a copolymer of polyethylene terephthalate (COPET), a copolymer of polybutylene terephthalate (COPBT), and a polyamide.

14. The non-woven composite fabric as claimed in claim 11 or 12, wherein the bi-component fiber of the melt spinning polymer is made of a material selected from the group consisting of polypropylene/polyethylene (PP/PE), polyethylene terephthalate/polyethylene (PET/PE), polyethylene terephthalate/polypropylene (PET/PP), polypropylene/a copolymer of polypropylene (PP/COPP), polyethylene terephthalate/a copolymer of polyethylene terephthalate

**EP 1 156 147 A1**

(PET/COPET), and a higher melting polyamide/a lower melting polyamide.

15. The non-woven composite fabric as claimed in claim 11 or 12, wherein the bi-component fiber of the melt spinning polymer includes a lower melting component and a higher melting component.

16. The non-woven composite fabric as claimed in claim 11 or 12, wherein the bi-component fiber of the melt spinning polymer is a micro fiber.

17. The non-woven composite fabric as claimed in claim 1, wherein the webs are consolidated by a method selected from the group consisting of thermo-bonding, hot air-through bonding, water-jet entangling, ultrasonic bonding, and high frequency wave bonding.

18. A process for preparing a non-woven composite fabric, comprising:

forming at least three webs, wherein at least one web is an air-laid web, and at least one web is a web selected from the group consisting of a spunbonded web and a meltblown web, and consolidating the at least three webs into the non-woven composite fabric.

EP 1 156 147 A1

European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 00 30 4179

## DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.)
X	US 5 979 030 A (LEGARE PIERRE) 9 November 1999 (1999-11-09) * column 5, line 30 - line 46; claims; figure 2 *	1-3, 11-13, 18	D04H13/00 B32B5/26 D04H5/00
X	US 5 886 306 A (PATEL KIRIT ET AL) 23 March 1999 (1999-03-23) * column 5, line 56 - line 64; example 4 *	1, 2, 4, 10-13, 17, 18	
Y	DE 299 13 054 U (SANDLER C H GMBH) 25 November 1999 (1999-11-25) * page 3 - page 5; claims; examples *	5-9, 14-16	
Y	US 5 879 343 A (DODGE II RICHARD NORRIS ET AL) 9 March 1999 (1999-03-09) * column 12, line 36 - line 47 *	5-9, 14-16	
A	WO 97 16148 A (POLY BOND INC) 9 May 1997 (1997-05-09) * figures 8, 9 *	1-18	
A	EP 0 285 338 A (GATES FORMED FIBRE PRODUCTS) 5 October 1988 (1988-10-05) * column 9, line 37 - line 54 *	1-18	TECHNICAL FIELDS SEARCHED (Int.Cl.) D04H B32B A61F

The present search report has been drawn up for all claims

EPO FORM 1503 (04/01) (P.0401)

Place of search	Date of completion of the search	Examiner
THE HAGUE	11 October 2000	Baratje, R
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date O : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document		

## EP 1 156 147 A1

ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.

EP 00 30 4179

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office (EPO) file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

11-10-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5979030 A	09-11-1999	CA 2224857 A	06-11-1997
		WO 9740913 A	06-11-1997
		EP 0848636 A	24-06-1998
		US 5898981 A	04-05-1999
US 5886306 A	23-03-1999	NONE	
DE 29913054 U	25-11-1999	NONE	
US 5879343 A	09-03-1999	AU 716607 B	02-03-2000
		AU 5360198 A	10-06-1998
		CN 1238670 A	15-12-1999
		EP 0951265 A	27-10-1999
		PL 333408 A	06-12-1999
		WO 9822066 A	28-05-1998
		US 5994615 A	30-11-1999
WO 9716148 A	09-05-1997	US 5643239 A	01-07-1997
		US 6114596 A	05-09-2000
		AU 7552896 A	22-05-1997
		CA 2236270 A	09-05-1997
		CN 1202814 A	23-12-1998
		EP 1005302 A	07-06-2000
		US 5928209 A	27-07-1999
EP 0285338 A	05-10-1988	US 4726987 A	23-02-1988
		US 4780359 A	25-10-1988
		AT 100505 T	15-02-1994
		BR 8801508 A	08-11-1988
		CA 1297654 A	24-03-1992
		DE 3887185 D	03-03-1994
		DE 3887185 T	21-07-1994
		IL 86046 A	05-11-1990
		JP 1077529 A	23-03-1989
		JP 1932642 C	26-05-1995
		JP 6059703 B	10-08-1994
		MX 166068 B	17-12-1992

EPO/COM/NEWS

For more details about this annex, see Official Journal of the European Patent Office, No. 12/82